

Technical Data Sheet Ricon® 183

Low Vinyl Butadiene-Styrene Copolymer

DESCRIPTION:

Ricon® 183 is a low molecular weight, liquid copolymer of butadiene and styrene. This resin is suitable for use in peroxide and sulfur-cured elastomers where it acts as a non-extractable plasticizer and process aid. Its polymeric structure gives excellent compatibility in saturated and unsaturated elastomers, especially elastomers with styrenic and aromatic content.

PRODUCT HIGHLIGHTS / PERFORMANCE PROPERTIES:

- Non-extractable process aid
- Electrical insulator
- Excellent dielectric properties
- Excellent hydrophobicity
- Low temperature flexibility
- Excellent compatibility with elastomers

SUGGESTED APPLICATIONS:

- Coatings
- Electronics
- Laminates
- Encapsulants
- Rubber
- Flexographic printing plates

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES:

Property	Test Method	Value	Unit
Molecular Weight (Mn)	QCS-651	3,200	g/mol
1,2 Vinyl Content*	QCS-642	30	wt. %
Viscosity @ 25°C	QCS-630	17,500	cps
Tg	QCS-681	-65	°C
Specific Gravity @ 25°C	QCS-649	0.90	-
Styrene Content	QCS-642	28	wt. %

*Butadiene portion

'CRAY VALLEY' is a brand name only. The Business Unit name 'TOTAL CRAY VALLEY' or the brand name 'CRAY VALLEY' may be used for promotion and/or sale of CRAY VALLEY products by Total Petrochemicals & Refining USA Inc. ("TPRI") or by Cray Valley SA, Cray Valley HSC Asia Limited, Cray Valley (Guangzhou) Chemical Co., Ltd, Cray Valley Italia S.r.l and Cray Valley Czech S.r.o. ("Cray Valley Legal Entities"). TPRI and each of the Cray Valley Legal Entities are independent entities (each are individually referred to as "SELLER"). The information contained in this document is believed to be true and accurate on the date issued. Seller reserves the right to make any changes to the product according to technological progress or further developments. **FINAL DETERMINATION OF SUITABILITY AND USE OF ANY PRODUCT FOR PROCESSING, USE, SALE, MARKETING, OR OTHER APPLICATION(S) IS THE SOLE RESPONSIBILITY OF THE BUYER/USER. IN NO EVENT WILL ANY SELLER ASSUME ANY LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN OR RELIANCE THERETO. SELLER MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, REGARDING THE PRODUCT OR THE INFORMATION CONTAINED IN THIS DOCUMENT, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS KNOWN TO SELLER. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF THE PRODUCT(S) FOR PROCESSING OR FOR BUYER'S/USER'S INTENDED USE, PROCESSING, APPLICATION, SALE, OR MARKETING. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, OF ANY TECHNICAL SUPPORT, ANY PROPRIETARY INFORMATION PROVIDED, OR THE RESULTS THAT MIGHT BE OBTAINED FROM TECHNICAL SUPPORT. ALTERATION OF THIS DOCUMENT IS STRICTLY PROHIBITED.** For further information please contact your local sales representative or visit www.crayvalley.com