

Technical Data Sheet Wingtack® 98

ALIPHATIC C-5 HYDROCARBON RESIN

DESCRIPTION:

Wingtack® 98 is a light colored, low odor aliphatic resin with excellent compatibility in less polar elastomers yielding adhesives with well balanced performance.

PRODUCT HIGHLIGHTS / PERFORMANCE PROPERTIES:

Compatible with less polar polymers, elastomers, e.g. Natural Rubber, Polyisoprene, SIS, and low VA EVA polymers.

SUGGESTED APPLICATIONS:

Hot melt adhesives (HMA)
Pressure sensitive adhesives (PSA)
Rubber processing
Sealants & Caulks
Plastics

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES:

Property	Test Method	Value	Unit
Appearance	Visual	Light yellow	-
Ash Content, wt.	TCV Method	<0.1	%
Color, Gardner, in 50% toluene	E-803	2.9	Gardner
Clarity	E-803a	95	%
Softening Point, R&B	E-950	98	°C
Specific Gravity @ 25 °C	ASTM D891	0.95	-
Tg (midpoint)	TCV Method	52	°C
Mn	TCV Method	1,000	g/mol
Mw	TCV Method	2,000	g/mol
EVA/Resin 1:1 Cloud Point			J
EVA (28% VA, 400 MFI)	TCV Method	188	°C
EVA (25% VA, 400 MFI)	TCV Method	150	°C
EVA (18% VA, 500 MFI)	TCV Method	70	°C

FDA Status: Wingtack® 98 may be permitted for use by one or more FDA regulations governing substances used in food-contact articles. Please contact your Technical Sales Representative to request a letter affirming the compliance to the regulation(s) that your application requires.

CRAY VALLEY is a brand name only. The Business Unit name 'TOTAL CRAY VALLEY or the brand name 'CRAY VALLEY' may be used for promotion and/or sale of CRAY VALLEY products by Total Petrochemicals & Refining USA Inc. ("TPRI") or by Cray Valley SA, Cray Valley HSC Asia Limited, Cray Valley (Guangzhou) Chemical Co., Itd, Cray Valley Italia S.r.I and Cray Valley Czech S.r.o. ("Cray Valley Legal Entities"). TPRI and each of the Cray Valley Legal Entities are independent entities (each are individually referred to as "SELLER"). The information contained in this document is believed to be true and accurate on the date issued. Seller reserves the right to make any changes to the product according to technological progress or further developments. FINAL DETERMINATION OF SUITABILITY AND USE OF ANY PRODUCT FOR PROCESSING, USE, SALE, MARKETING, OR OTHER APPLICATION(S) IS THE SOLE RESPONSIBILITY OF THE BUYER/USER. IN NO EVENT WILL ANY SELLER ASSUME ANY LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN OR RELIANCE THERETO. SELLER MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, REGARDING THE PRODUCT OR THE INFORMATION CONTAINED IN THIS DOCUMENT, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS KNOWN TO SELLER. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF THE PRODUCT(S) FOR PROCESSING OR FOR BUYER'S/USER'S INTENDED USE, PROCESSING, APPLICATION, SALE, OR MARKETING. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, OF ANY TECHNICAL SUPPORT, ANY PROPRIETARY INFORMATION PROVIDED, OR THE RESULTS THAT MIGHT BE OBTAINED FROM TECHNICAL SUPPORT. ALTERATION OF THIS DOCUMENT IS STRICLTY PROHIBITED. For further information please contact your local sales representative or visit www.crayvalley.com

