

Viscosity of Ricon® Products at Various Temperatures

Viscosity (in cps) vs Temperature											
Ricon® Product											
	Ricon® 100	Ricon® 130	Ricon® 131	Ricon® 134	Ricon® 150	Ricon® 152	Ricon® 153	Ricon® 154	Ricon® 156	Ricobond® 1756	Ricobond® 1731
% vinyl	70	30	30	35	70	80	85	90	70	70	30
MW _n	4500	2500	4200	9000	3900	2900	4700	5200	1400	1700	5100
Temp. °C											
25	380000	750	2750	16000	34200				1600		300000
30	160500	689		13000		74400	262000				235000
35				9600	23000						158000
40	45300	444		7600		32000	87000				105000
45	36000			6000	10800	25000	55000	270000			59000
50	19000	307		4600		20300	34100				42500
55				3800	5050			113000		194000	32000
60	8750	208		3000		13250	14900				22800
65				2500	2600			46400		66000	14000
70	4410	158		2100		2880	7350				8560
75				1800	1490			21000		20000	5950
80	2410	122		1500		1580	4010				4290
85				1300	886			10200		8400	3170
90	1470	98		1200		940	2130				2430
95				1100	542			5300		3970	1910
100	990	83		940		620	1400				1450
105								2920		1980	

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond Cray Valley Company's control. The listed properties are illustrative only, and not product specifications. Cray Valley Company disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.

Oaklands Corporate Center, 468 Thomas Jones Way, Suite 100, Exton, PA 19341
Toll Free 877-871-2729

