

# CRAY VALLEY

## Technical Data Sheet

# CLEARTACK® W100

## HYDROCARBON RESIN

### DESCRIPTION

Cleartack® W100 is a water white pellet, low odor, pure styrenic monomer resin that is produced by cationic polymerization.

### PRODUCT HIGHLIGHTS / PERFORMANCE PROPERTIES

Good thermal stability  
Good compatibility with many polymers and resins  
Good solubility with most common solvents  
Good tackifying characteristics  
Water white color  
Efficient plasticizer in styrenic elastomers  
Good Color Stability for 72 hrs. @ 177°C (350°F)  
Improvement of tack

### SUGGESTED APPLICATIONS

Hot melt adhesives (HMA)  
Pressure sensitive adhesives (PSA)  
Coatings & Paints  
Plastics & Rubber  
Sealants

### TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Property	Test Method	Value	Unit
Appearance	Visual	Colorless solid	
Color, 50% toluene	Based on ASTM D3461	<40	Hazen
Softening Point, R&B	Based on ISO 6271	100	°C
Specific Gravity, 20/20	ASTM D891	1.06	g/cc
Acid number	ASTM D664	<0.1	mg KOH/g

**Regulatory Notice:** CLEARTACK® W100 may be permitted for use by one or more FDA regulations governing substances used in food-contact articles. Please contact your Technical Sales Representative to request a letter affirming the compliance to the regulation(s) that your application requires.



'CRAY VALLEY' is a brand name only. The Business Unit name 'CRAY VALLEY' or the brand name 'CRAY VALLEY' may be used for promotion and/or sale of CRAY VALLEY products by TotalEnergies Petrochemicals & Refining USA Inc. ('TEPRI') or by Cray Valley SA, Cray Valley HSC Asia Limited, Cray Valley (Guangzhou) Chemical Co., Ltd, Cray Valley Italia S.r.l and Cray Valley Czech S.r.o. ('Cray Valley Legal Entities'). TEPRI and each of the Cray Valley Legal Entities are independent entities (each are individually referred to as "SELLER"). The information contained in this document is believed to be true and accurate on the date issued. Seller reserves the right to make any changes to the product according to technological progress or further developments. FINAL DETERMINATION OF SUITABILITY AND USE OF ANY PRODUCT FOR PROCESSING, USE, SALE, MARKETING, OR OTHER APPLICATION(S) IS THE SOLE RESPONSIBILITY OF THE BUYER/USER. IN NO EVENT WILL ANY SELLER ASSUME ANY LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN OR RELIANCE THERETO. SELLER MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, REGARDING THE PRODUCT OR THE INFORMATION CONTAINED IN THIS DOCUMENT, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS KNOWN TO SELLER. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF THE PRODUCT(S) FOR PROCESSING OR FOR BUYER'S/USER'S INTENDED USE, PROCESSING, APPLICATION, SALE, OR MARKETING. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED, OF ANY TECHNICAL SUPPORT, ANY PROPRIETARY INFORMATION PROVIDED, OR THE RESULTS THAT MIGHT BE OBTAINED FROM TECHNICAL SUPPORT. ALTERATION OF THIS DOCUMENT IS STRICTLY PROHIBITED. For further information please contact your local sales representative or visit [www.crayvalley.com](http://www.crayvalley.com)